



# Wanda Elastic Additive


Smart Look. Smart Choice.

FOR PROFESSIONAL USE ONLY

## Description

Wanda Elastic Additive is designed to promote primers and clears flexibility on very flexible plastic parts. For rigid plastic, no additive is required.

### Mixing Ratio:



Products	Elastic Additive
Wanda Low VOC Primer – As a high build primer	10%
Wanda Low VOC Primer – As a wet-on-wet non-sanding sealer	0%
Wanda Low VOC Clear	10%

### Do not use Elastic Additive in Wanda Waterbase.



Use suitable respiratory protection  
Akzo Nobel Car Refinishes Inc. recommends the use of a fresh air supply respirator

Read complete TDS for detailed product information





# Wanda Elastic Additive

Smart Look. Smart Choice.

FOR PROFESSIONAL USE ONLY

## Description

Wanda Elastic Additive is designed to promote primers and clears flexibility on very flexible plastic parts. For rigid plastic, no additive is required.


## Products and additives

- Product:** - Wanda Elastic Additive
- Activators / Reducers:** - None
- Additives:** - None

## Basic raw materials

- Wanda Elastic Additive: Polyester resin and solvents.


## Material preparation and mixing



Products	Elastic Additive
Wanda Low VOC Primer – As a high build primer	10%
Wanda Low VOC Primer – As a wet-on-wet non-sanding sealer	0%
Wanda Low VOC Clear	10%

**Do not use Elastic Additive in Wanda Waterbase.**

## Spray Viscosity



12–14 seconds DIN cup #4 at 70°F (20°C).

## Spray application



**Wanda Low VOC Primer:** add 10% of Elastic Additive (volume) to Wanda Low VOC Primer prior to activating and reducing. Follow with the primer mixing ratio.

**Wanda Low VOC Clear:** add 10% of Elastic Additive (volume) to Wanda Low VOC Clear prior to activating and reducing. Follow with clear mixing ratio.

## Application process



Follow the specific process of the product that the Elastic Additive is being used with.





Smart Look. Smart Choice.

North America

Technical Data Sheet  
2.2.2011

# Wanda Elastic Additive

FOR PROFESSIONAL USE ONLY

## VOC

The VOC content of this product is 0 lb. /gallon.

## Storage

Product shelf-life is determined when products are stored unopened.  
Shelf life: 3 years at 70°F and 95°F (20°C and 35°C)

## Notes

Elastic Additive must be added to the product prior to activating and reducing.

---

**AkzoNobel Car Refinishes Inc. North America**

**Address: 5555 Spalding Drive, Norcross. GA 30092 USA**

**Tel: 770-662-8464**

---

### FOR PROFESSIONAL USE ONLY

**IMPORTANT NOTE:** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

**Head Office**

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands.

