




## **7200 1K PU SEALANT**

ET/PU-7200B, 310ml black ET/PU-7200G, 310ml grey ET/PU-7200W, 310ml white

_		
	_ 1	
П	= 1	
П		
П		
П	_	





Substrates	welded seams, flanges, car doors, baggage compartment, painted plastics.

Clean, dry and degrease the surface. Pre treat metal surfaces with anti-corrosive primer if needed.



**Surface Preparation** 

Hardness shore A 55-60 DIN 53505

Tensile strength 2.0± 0,1 N/mm<sup>2</sup> DIN 53504

Elongation at break ≥300% DIN 53504

**Specific weight**  $1,26 \pm 0,02 \text{gr/cc}$ 



Over paintable: ≈ 45min

Complete curing: up to 5mm in 24hr

Shelf life 12 months

Technical Data Sheet etalon-refinish.com