













970 2:1 UHS CLEARCOAT

ET970-UHS01 1L
ET970-UHS05 5L

	Product	Premium quality ultra high solids clearcoat. Deep shine, good flow and fast drying properties.
	Substrates	Apply on top of fully dry solvent and waterborne basecoats
	Surface Preparation	The use of tack cloth is recommended prior application
	Application Conditions	18-22°C
	Mixing	2:1 by volume with Etalon UHS hardener slow, normal, fast or extrafast
	Dilution	0-10% with acrylic reducer (thinner)
	Pot Life	30-50 min at 20°C
	Application Viscosity	19-23 sec at 20°C Ford cup 4
	Spraying Equipment	Gravity feed spray gun 1.3mm
	Number of layers	2 coats
	Flash off	7-10 min
	Coating Thickness	50-60 µm
	Drying	30 min at 60°C
	Drying with IR lamps	12-15 min
	VOC	Compliant < 420 g/l
	Shelf life	18 months