



990 2:1 SR HS CLEARCOAT

ET990-SR011L ET990-SR055L

i	Product	2K scratch resistant high solids acrylic clearcoat. Fast drying, non-yellowing UV resistant formula.
	Substrates	Apply on top of fully dry solvent and waterborne basecoats
	Surface Preparation	The use of tack cloth is recommended prior application
	Application Conditions	18-22°C
	Mixing	2:1 by volume with Etalon hardener ET991 slow and normal
	Dilution	No dilution required
	Pot Life	up to 1,5 hours at 20°C
s	Application Viscosity	14-16 sec at 20°C Ford cup 4
*	Spraying Equipment	Gravity feed spray gun 1.3mm
	Number of layers	2 coats
<u>/</u> †/†/	Flash off	5-10 min
	Coating Thickness	45-50 μm
	Drying	15 min at 60°C
	Drying with IR lamps	7-10 min
	voc	2004/42/IIB€(840)<840
	Shelf life	18 months

Technical Data Sheet etalon-refinish.com