

# Perfeccoat

## PC-6400 SUPER FAST CLEARCOAT(4:1)

### DESCRIPTION:

Perfeccoat PC-6400 Super Fast Clearcoat(4:1) is eco-friendly two-pack extra fast drying clear coat with certain amount of exempt solvent, made from modified acrylic polyols, low VOC emission, high gloss, suitable for metal surface.

### COMPONENTS:

PC-6400	Super Fast Clearcoat (4:1)	
PC-6401	Fast Activator	<64°F
PC-6402	Standard Activator	64-86° F
PC-6403	Slow Activator	>86° F

### SUBSTRATES:


1K basecoat

### SURFACE PREPARATION:




Remove wax, silicon or other contaminations with 3910 Degreaser.

### MIX RATIO:



PC-6400 4 parts  
PC-6401/6402/6403 1 part

### POT LIFE:



Use in an hour @ 73° F after mixing.

### ADDITIVES:

- Blushing: 3960 Retarder Solvent over 86° F. Refer to tech sheet of Retarder Solvent for details.
- Fisheyes: 3930 Anti Silicon (0.5-1%) in the paint remained and re-spray the affected area.
- Overspray: 3920 Thinner SRA. Refer to tech sheet of Thinner SRA for details.

### APPLICATION:




Spray gun set up and pressure:

RP : 1.3mm 29-36psi

HVLP : 1.3mm 26-29psi

Please refer to gun

manufacturer for proper spray pressure recommendations.



Coats & Thickness:  
2 Coats, about 40-60pm  
No Flash off time.

### DRY TIME:



@ 59°F

Dust free: 20-30 minutes

Dry to Polish: 60 minutes

@ 73°F

Dust free: 15-20 minutes

Dry to Polish: 40 minutes

@ 140°F

Dust free: 5 minutes

Dry to Polish: 10 minutes



### CLEARNING:

Clean equipment immediately with solvent after application

### Re-application

If there are particles or runs after spray, wet sand the affected area with P2000 sand paper after thorough drying, then polish to solve the problem.

### Note:

- When ambient temperature is lower than 41°F, to fast the film drying time, allow a full bake at 140°F.
- The products mixed with hardener should be used up within 0.5 hour.
- Shelf Life: 2 years in original sealed can at cool and dry place at 41-95°F.

### PHYSICAL DATA:

VOC: 4.3 lbs/gal

### FOR PROFESSIONAL USE ONLY

Read MSDS Before Use

NOTE: The information in this data sheet is based on our knowledge and the current laws. It is always the responsibility of the user to fulfill the requirements of local rules and legislations. The uncertain factors may affect the application of products, such as the condition of substrate. We do not accept any liability on loss, damage and performance of products unless we issue a special agreement. Always read the latest Material Data Sheet and the Technical Data sheet before applying the products.