

The United States of America:
Peter Kwasny Inc.
62-64 Enter Lane,
Islandia, NY 11749

Distributed in

Canada by
Peter Kwasny Spraypaint Canada Inc.
2275 Lakeshore Blvd. West, Suite 530
Toronto, ON. M8V 3Y3

Toll free North America
Phone: 1-844-426-6330 / Fax: 1-866-226-6434
order@kwasny.us / service@kwasny.us
www.spraymax.com

SprayMax®
1K TEXTURE COATING BLACK
384 g NET WT. 13.5 oz
Art. Nr. 3680224



Product

Description / Purpose

Special product for imitation of automotive plastic textured surfaces, particularly for plastic bumpers, trim strips and various plastic parts

Properties

- different kind of structures can be achieved
- Easy to use
- Dries very quickly
- Can be topcoated with all conventional 1K basecoat solventborne and waterborne and 2K topcoat systems

Material base

Special resin combination

Colour

Black

Solid content

approx. 50,6 % by weight relating to the diluted paint

EPA Coating Category

ABT Automotive Bumper and Trim Products
PWR Limit 1.75

CARB Aerosol Rule Coating Category (01/2017)

ABT Automotive Bumper and Trim Products
PWR Limit 1.70

Substrate

Polypropylene (PP/EPDM), Polyvinyl Chloride (PVC), Acrylic nitrile butadiene styrene (ABS) and other Plastics. (cleaned and sanded)

In case of doubt, the compatibility of the paint for the respective substrate must be pretested and, if necessary, a suitable pre-treatment with SprayMax plastic adhesion promotor 3680009 must be chosen.

Sand surfaces if necessary and clean thoroughly with SprayMax 1k Solvent Wash 3680090. Check compatibility and adhesion first on an unobtrusive area.


Processing

Protection measures




Wear personal protection equipment. (respiratory mask / gloves / goggles)
For more information, see safety data sheet.

Shake




Shake can thoroughly for at least 2 minutes from when the agitation balls are heard.

Adjustable Nozzle




Set the variable spray nozzle to the size and pattern of the damage.

Spray to test




After shaking the can, test spray and check compatibility with the surface and the colour.

Spraying distance




6 - 8 inches / 15 - 20 cm
Depending on the desired structure, the spray distance and speed should be varied.

Spray passes



Dry film thickness 1.2 - 1.6 mil (30 - 40µm)
(approx. 2 - 3 spray coats)

Flash-off time




Flash time: approx. 5 - 10 min between each spray coat

Processing conditions




Optimum application at 64° F - 77° F (18° C - 25° C) and a relative humidity from 40 - 50 %.

Coverage



approx. 5.4 - 8 sq ft (0.5 m² - 0.75 m²) / aerosol at approx. 1.2 - 1.6 mil (30 - 40 µm) dry film thickness.

Drying



dust dry: 15 min
dry to touch: approx. 30 - 40 min
fully cured: approx. 24 h

The stated values refer to the above mentioned processing conditions. The level of dryness is determined pursuant to DIN 53150.




IR drying possible,
Respect technical manual

Continue

Can be topcoated with itself after 15 min and with all conventional 1K basecoat solventborne and waterborne and 2K topcoat systems.

Finish




After painting, turn the can upside down and spray the valve until empty.

Additional Information

Important Information

Not suitable for plastic parts made from PE. Do not apply to surfaces coated with synthetic resin paints as this could lift and cause ripples in the paintwork underneath.

Shelf Life



60 months

The usage period refers to an unused can that is stored correctly at a temperature of 60° F - 77° F / 15 - 25° C and a relative humidity below 60 %. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

Disposal



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

Note

For professional use only.

Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved. We reserve the right to update, amend or supplement the content of the information without prior notice.